

TECHNICAL DATA SHEET

Date of Issue 03/2026 | Rev. 00_03/2026

6260 Entry Level Body Shop Masking Tape



PRODUCT DESCRIPTION

6260 Entry Level is a general-purpose masking tape designed for basic car refinishing operations. Made with a saturated crepe paper backing and a natural rubber adhesive, it provides reliable adhesion on painted metal, glass, and rubber during spray-painting and drying cycles up to 60°C. It ensures clean removal without residue and good holding power even when overlapped with masking paper or film. FSC® certified paper makes it a sustainable choice for automotive and repair workshops requiring dependable everyday performance.

FEATURES

- Temperature resistance up to 60°C (140°F)
- Reliable adhesion on metal, glass, and rubber
- Clean removal after drying cycles
- Compatible with masking paper and film
- Good holding power for basic refinishing jobs
- FSC® certified paper backing

MAIN APPLICATIONS

- Basic spray-painting in car repair and refinishing
- Masking during drying cycles up to 60°C
- Suitable for short body shop processes
- General automotive maintenance and touch-ups

CONSTRUCTION

	Adhesive	Backing
Material	Natural rubber	Saturated crepe paper
Colour	<input checked="" type="radio"/> Transparent	<input type="radio"/> White <input checked="" type="radio"/> Sharp Yellow <input type="radio"/> Honey <input checked="" type="radio"/> Brown

TECHNICAL DATA*

	Metric	Imperial Units	Test Method
Total weight	80 g/m ²	2.36 oz/yd ²	ISO 536
Total thickness	110 µm	4.3 mils	Internal
MD tensile strength	34 N/cm	19.4 lb/in	AFERA 5004/PSTC 131
MD elongation at break	8 %	8 %	AFERA 5004/PSTC 131
Adhesion to steel plate	1.6 N/cm	14.6 oz/in	AFERA 5001/PSTC 101
Temperature resistance	60°C (30 min)	140°F (30 min)	

*Typical value

All technical data provided is based on laboratory testing and is believed to be accurate. End users are responsible for determining product suitability for their intended application.

Technical Information and Product Use

All technical information and data above mentioned are provided to the best of our knowledge on the basis of our practical experience. Figures shown refer to average values only, based on tests carried out in conditioned laboratory and are not valid for specification. The company reserves the right to modify or change the products at any time without notice. The accuracy or completeness of such information is not guaranteed. The technical information, suggestions and other statements contained in this document have been compiled for your guidance and usage. ATLAS Tapes Group reminds the user of the products to make sure that the product is used as per the instructions and suggestions provided. It is the user's sole responsibility to determine the suitability of the product in actual application under specific conditions.

Storage and Shelf Life

Suggested storage in dry area away from direct sunlight temperature should range from 59°F / 15°C to 77°F / 25°C with max relative humidity of 50%. Tape and jumbo roll should be used respectively within 12 months and 6 months from date of shipment. ATLAS Tapes Group does not take responsibility for the defective material if is not stored and used in accordance with the conditions listed above.